


Dry molding process / La-Co type

### FB5D

Demagnetization curve



#### Magnetic characteristics

Material	FB5D	
Residual magnetic flux density $B_r$	(mT)	$415 \pm 10$ (4.15 ± 0.1 kG)
Coercive force $H_{CB}$	(kA/m)	$254.6 \pm 12$ (3.2 ± 0.15 kOe)
Intrinsic coercive force $H_{CJ}$	(kA/m)	$262.6 \pm 16$ (3.3 ± 0.2 kOe)
Maximum energy product (BH)max	(kJ/m³)	$32.6 \pm 1.6$ (4.1 ± 0.2 MGOe)