


Dry molding process / La-Co type

FB5DH

Demagnetization curve



Magnetic characteristics

| Material | FB5DH | |
|--------------------------------------|---------|---------------------------------|
| Residual magnetic flux density B_r | (mT) | 400 ± 10 (4.00 ± 0.1 kG) |
| Coercive force H_{CB} | (kA/m) | 278.6 ± 12 (3.5 ± 0.15 kOe) |
| Intrinsic coercive force H_{CJ} | (kA/m) | 318.3 ± 16 (4.0 ± 0.2 kOe) |
| Maximum energy product (BH)max | (kJ/m³) | 30.3 ± 1.6 (3.8 ± 0.2 MGOe) |