


FB Series

Wet molding process / La-Co free type

FB6H

Demagnetization curve



Magnetic characteristics

Material	FB6H	
Residual magnetic flux density B_r	(mT)	400 ± 10 (4.0 ± 0.1 kG)
Coercive force H_{CB}	(kA/m)	302.4 ± 12 (3.8 ± 0.15 kOe)
Intrinsic coercive force H_{CJ}	(kA/m)	358.1 ± 12 (4.5 ± 0.15 kOe)
Maximum energy product (BH)max	(kJ/m³)	30.3 ± 1.6 (3.8 ± 0.2 MGOe)

△ The details can be found by referring to the appended individual delivery specifications.
All specifications are subject to change without notice.