


FB Series

Wet molding process / Higher power La-Co free type FB9BF

Demagnetization curve



Magnetic characteristics

Material	FB9BF		
Residual magnetic flux density B_r	(mT)	435 ± 10	$(4.35 \pm 0.1 \text{ kG})$
Coercive force H_{CB}	(kA/m)	315 ± 12	$(3.96 \pm 0.15 \text{ kOe})$
Intrinsic coercive force H_{CJ}	(kA/m)	340 ± 12	$(4.27 \pm 0.15 \text{ kOe})$
Maximum energy product $(BH)_{max}$	(kJ/m ³)	36.3 ± 1.6	$(4.56 \pm 0.2 \text{ MGOe})$

△ The details can be found by referring to the appended individual delivery specifications.
All specifications are subject to change without notice.