


## FB Series

### Wet molding process / Higher power La-Co type FB9H

Demagnetization curve



#### Magnetic characteristics

Material	FB9H		
Residual magnetic flux density $B_r$	(mT)	$430 \pm 10$	$(4.3 \pm 0.1 \text{ kG})$
Coercive force $H_{cB}$	(kA/m)	$330.2 \pm 12$	$(4.15 \pm 0.15 \text{ kOe})$
Intrinsic coercive force $H_{cJ}$	(kA/m)	$397.9 \pm 12$	$(5.0 \pm 0.15 \text{ kOe})$
Maximum energy product $(BH)_{max}$	(kJ/m <sup>3</sup> )	$35.0 \pm 1.6$	$(4.4 \pm 0.2 \text{ MGOe})$

△ The details can be found by referring to the appended individual delivery specifications.  
All specifications are subject to change without notice.