


Wet molding process / Higher power La-Co free type FB9HF

Demagnetization curve



Magnetic characteristics

Material	FB9HF		
Residual magnetic flux density B_r	(mT)	405 ± 10	$(4.05 \pm 0.1 \text{ kG})$
Coercive force H_{CB}	(kA/m)	310 ± 12	$(3.90 \pm 0.15 \text{ kOe})$
Intrinsic coercive force H_{CJ}	(kA/m)	400 ± 12	$(5.03 \pm 0.15 \text{ kOe})$
Maximum energy product $(BH)_{max}$	(kJ/m³)	31.7 ± 1.6	$(3.39 \pm 0.2 \text{ MGOe})$