


## FB Series

### Dry molding process / La-Co free type FB3N

Demagnetization curve



#### Magnetic characteristics

Material	FB3N		
Residual magnetic flux density $B_r$	(mT)	$395 \pm 15$	$(3.95 \pm 0.15 \text{ kG})$
Coercive force $H_{CB}$	(kA/m)	$234.8 \pm 12$	$(2.95 \pm 0.15 \text{ kOe})$
Intrinsic coercive force $H_{CJ}$	(kA/m)	$238.7 \pm 16$	$(3.0 \pm 0.2 \text{ kOe})$
Maximum energy product $(BH)_{max}$	(kJ/m <sup>3</sup> )	$28.7 \pm 2.4$	$(3.6 \pm 0.3 \text{ MGOe})$

△ The details can be found by referring to the appended individual delivery specifications.  
All specifications are subject to change without notice.