


FB Series

Wet molding process / Higher power La-Co type FB9B

Demagnetization curve



Magnetic characteristics

Material	FB9B		
Residual magnetic flux density B_r	(mT)	450 ± 10	$(4.50 \pm 0.1 \text{ kG})$
Coercive force H_{cB}	(kA/m)	342.2 ± 12	$(4.3 \pm 0.15 \text{ kOe})$
Intrinsic coercive force H_{cJ}	(kA/m)	358.1 ± 12	$(4.5 \pm 0.15 \text{ kOe})$
Maximum energy product $(BH)_{max}$	(kJ/m ³)	38.6 ± 1.6	$(4.9 \pm 0.2 \text{ MGOe})$

△ The details can be found by referring to the appended individual delivery specifications.
All specifications are subject to change without notice.